

CE Produkter AB
c/o Berit Ekman Hantverksgatan 2
314 52 UNNARYD

Reaction to fire classification report

1 Introduction

This classification report defines the classification assigned to the product called “SOUNDFELT VF GRÅ” respectively “SOUNDFELT VF” in accordance with the procedure given in EN 13501-1:2007+A1:2009.

This classification report replace SP classification report 3P01481-2, dated August 9, 2013. The name of the product has been changed.

2 Details of classified product

2.1 General

The products is defined as an acoustic insulation.

2.2 Product description

According to the client:

Wadding for ventilation and sound absorbing called “SOUNDFELT VF GRÅ” respectively “SOUNDFELT VF”, consisting of thermo bonded polyester fibre with a facing of non-woven polyester. The facing has a nominal area weight of 45 g/m². The product has a nominal area weight range of 400 – 2600 g/m² and a nominal range of 6 – 50 mm.

3 Test reports & test results in support of classification

3.1 Test reports

This classification is based on the test reports listed below:

Name of laboratory	Name of sponsor	Test report ref no	Accredited test method
SP	CE Produkter AB	P601926	EN 13823 EN ISO 11925-2
SP	CE Produkter AB	3P01481	EN 13823 EN ISO 11925-2

RISE Research Institutes of Sweden AB

Postal address
Box 857
SE-501 15 BORÅS
SwedenOffice location
Brinellgatan 4
SE-504 62 BORÅSPhone / Fax / E-mail
+46 10 516 50 00
+46 33 13 55 02
info@ri.se

This report may not be reproduced other than in full, except with the prior written approval of the issuing laboratory.

3.2 Test results

The test results listed below show the worst case as found in the test programme performed and reported according to the table above. The tests have been carried out on products covering the area weight range and thickness range of the product group.

Test method	Parameter	Number of tests	Results	
			Continuous parameter mean (m)	Compliance with parameters
EN ISO 11925-2		16		
Edge/Surface flame attack**				
30 s exposure	$F_s \leq 150 \text{ mm}$		(-)	Compliant
Flaming droplets/particles	Ignition of filter paper		(-)	No ignition of filter paper
EN 13823		3		
	$FIGRA_{0,2MJ} \text{ (W/s)}$		20	Compliant
	$FIGRA_{0,4MJ} \text{ (W/s)}$		20	Compliant
	$LFS < \text{edge}$		(-)	Compliant
	$THR_{600s,} \text{ (MJ)}$		2.1	Compliant
	$SMOGRA, \text{ (m}^2/\text{s}^2\text{)}$		4	Compliant
	$TSP_{600s,} \text{ (m}^2\text{)}$		44	Compliant
	Flaming droplets/particles		(-)	No flaming droplets/particles

** : as required to the end use application of the product

(-) : not applicable

4 Classification and field of application

4.1 Reference and direct field of application

This classification has been carried out in accordance with clause 11 and 15 of EN 13501-1:2007+A1:2009.

4.2 Classification

The product called “SOUNDFELT VF GRÅ” respectively “SOUNDFELT VF” in relation to its reaction to fire behaviour is classified:

B

The additional classification in relation to smoke production is:

s1

The additional classification in relation to flaming particles/droplets is:

d0

The format of the reaction to fire classification for construction products excluding floorings and linear pipe thermal insulation product is:

Fire Behaviour		Smoke Production			Flaming Droplets	
B	-	s	1	,	d	0

Reaction to fire classification: *B-s1,d0*

4.3 Field of application:

This classification is valid for the following product parameters:

Nominal thickness: 6 – 50 mm.

Nominal area weight: 400 – 2600 g/m²

This classification is valid for the following end use conditions:

Mounting

- Freestanding with an air gap of ≥80 mm.

Joints

- Horizontal and vertical joints.

The sample was delivered by the client. RISE Fire Research was not involved in the sampling procedure.

5 Limitations

This classification document does not represent type approval or certification of the product.

RISE Research Institutes of Sweden AB **Safety - Fire Research, Fire Dynamics**

Performed by

Examined by

Richard Johansson

Per Thureson